



## GENEL ÜRÜN ANALIZI

Analizler	Değerler	Test Metotları
Pigment Adı ve Kodu	Çinko Tetraoksit Kromat ZTC-19	
Renk Indisi	PY36/77955	
Dökme Yoğunluğu(g/cm <sup>3</sup> ) ± 15 %	0,3 – 0,5	ISO 787-11
Sıkıştırılmış Dökme Yoğunluğu(g/cm <sup>3</sup> )	0,7 – 1,0	ISO 787-11
Yağ Absorpsiyonu (g/100 g) ± 15 %	17 – 23	ISO 787-5
pH ± 1	7	ISO 787-9
Nem ve uçucu Madde(105°C) max, %	0.5	ISO 787-2
44 µ Elek Bakiyesi max, %	0.5	ISO 787-7
Suda Çözünen Madde max, %	0.5	ISO 787-3
İsi Stabilitesi, °C	160	ISO 787-21
ZnO min, %	69 – 72	ISO 1249
CrO <sub>3</sub> min.,%	17 – 19	ISO 1249

TECHNICAL  
DATA  
SHEET



Kemalpaşa Asfaltı No.44 Kemalpaşa-İzmir  
Tel:0232. 877 04 00 • Fax:0232. 877 04 01 • web:http://www.pigment.com.tr • e-mail:pigment@pigment.com.tr • e-mail:info@pigment.com.tr

This information is based on our present state of knowledge and is intended to provide general notes on our products and their application. It should not therefore be construed as guaranteeing specific properties of the described or their suitability for a particular application. Any existing industrial property rights must be observed. The quality of our products is guaranteed under our General Conditions of Sale.