



GENEL ÜRÜN ANALIZI

Analizler	Değerler	Test Metotları
Pigment Adı ve Kodu	Siyah Demir Oksit BLK-101-MG	
Renk Indisi	PBI.11/77499	
Özgül Yoğunluğu (g/cm ³)	4.5	ISO 787-10
Dökme Yoğunluğu(g/cm ³) ± 15 %	0.5 – 0.7	ISO 787-11
Sikistirilmiş Dökme Yoğunluğu(g/cm ³)	1.1 – 1.5	ISO 787-11
Yag Absorpsiyonu (g/100 g) ± 15 %	13 – 18	ISO 787-5
pH ± 1	7.0	ISO 787-9
Nem ve uçucu Madde(105°C) max, %	1.0	ISO 787-2
44 µ Elek Bakiyesi max, %	0.2	ISO 787-7
Tanecik boyutu, mikron d90 max.	2,0	*ISO 8130-13
Suda Çözünen Madde max, %	0.5	ISO 787-3
Isi Stabilitesi, °C	200	ISO 787-21
Isik Haslıđı (1-8 ölçek)	7 – 8	ISO 787-15
Demir Oksit Fe ₂ O ₃ min.%	92 – 95	ISO 1248

* Cilas 850 Tane dağılım cihazıyla ölçülmüştür.

TECHNICAL
DATA
SHEET



Kemalpaşa Asfaltı No.44 Kemalpaşa-İzmir
Tel:0232. 877 04 00 • Fax:0232. 877 04 01 • web:http://www.pigment.com.tr • e-mail:pigment@pigment.com.tr • e-mail:info@pigment.com.tr

This information is based on our present state of knowledge and is intended to provide general notes on our products and their application. It should not therefore be construed as guaranteeing specific properties of the described or their suitability for a particular application. Any existing industrial property rights must be observed. The quality of our products is guaranteed under our General Conditions of Sale.